

# TEST REPORT -16768

## Assured Testing Services

198 River Road Ridgway, PA 15853 USA  
 Ph: (814) 773-3224 Fax (814) 773-3225  
 michelesinger@assuredtestingservices.com



A2LA CERT# 2012.01  
 ISO 17025 Accredited

### CLIENT BILL TO

<b>BILL TO:</b> PARENO--0044	OurSupplier ID
Metalife Industries	
141 Mong Way	
P.O. Box 53	
Reno PA 16343	
USA	
	Supplier Code Ph: 800-327-9413

### CLIENT SENT TO

<b>SENT TO:</b> PARENO--0044	OurSupplier ID
Metalife Industries	
141 Mong Way	
P.O. Box 53	
Reno PA 16343	
USA	
	Supplier Code Ph: 800-327-9413

**Test Report#: 16768**    **Entry Date:** Tuesday, February 23, 2016

**Contact:** Andy Kockler

**PO#:** PUR560

*Measurement of coating thickness on coated metal pin IAW ASTM B487.*

Part Test Information										
PART NUMBER	LOT NUMBER	S#	SAMPLE DESCRIPTION			HOURS		CYCLES		
TEST SPECIFICATION NAME			TEST PROCEDURE NAME			REQ	COMP	REQ	HOURS	COMP
<b>Metal Pin</b>	5.25" x 1.25" diameter		Unspecified	Thickness ASTM B487 Cross Section Examination						
			23-Feb-16	29-Feb-16	1	0				
<i>Results:</i>										
<i>Coating Measurements – 0.00016, 0.00016, 0.00016, 0.00016, 0.0016 inches</i>										
<i>Average Coating Thickness – 0.00016 inches</i>										
<i>See attachment for detail and photomicrograph of coating section.</i>										

Michele Singer

Revision# 1.10 Date 12/16/10

End Of Report

Quality Assurance Administrator

The results stated above relate only to the specific items tested. Information and statements in this report are derived from material, information, and/or specifications furnished by the client and exclude any expressed or implied warranties as to the fitness of material tested or analyzed for any particular purpose or use. This report is confidential property of our client and may not be used for advertising purposes. This report shall not be reproduced except in full, without written approval of this laboratory. This recording of false, fictitious or fraudulent statements or entries on this document may be punished as a felony. Sample remnants are retained for a minimum of 6 months following issuance of test results, at which point they will be discarded unless notified in writing by the client. Any client claims or damages arising from the use of information in this report are strictly limited to the cost of the services provided by Assured Testing Services.

www.assuredtestingservices.com

198 River Road  
Ridgway, PA 15853 USA  
P: +1 814-773-3224  
F: +1 814-773-3225

## Test Report TR16768

29 February 2016

**Customer:** Metalife Industries

**PO:** PUR560

**Contact:** Andy Kockler

**Telephone:** 1-800-327-9413


**Description:** Evaluation of coating thickness on a metal pin sample.

**Results:**

**Coating Thickness**

Coating Measurements – 0.00016, 0.00016, 0.00016, 0.00016, 0.00016 inches

Average Coating Thickness – 0.00016 inches



**Notes:**

1. The coating measurements were taken at 1000X.
2. Photomicrograph of the coating is provided below the measurements of the sample.

**Observations and Interpretations:** None.

**Test Method(s) Used:** ASTM B487, E883

**End of TR16768 Photo Pages**