

# TEST REPORT -8672

## Assured Testing Services

198 River Road Ridgway, PA 15853 USA  
 Ph: (814) 773-3224 Fax (814) 773-3225  
 michelesinger@assuredtestingservices.com



TESTING CERT# 2012.01

### CLIENT BILL TO

### CLIENT SENT TO

ISO 17025 Certified

<b>BILL TO:</b> PARENO--0044	OurSupplier ID
Metalife Industries	
141 Mong Way	
P.O. Box 53	
Reno PA 16343	
USA	Supplier Code
Attn:	Ph: 800-327-9413

<b>SENT TO:</b> PARENO--0044	OurSupplier ID
Metalife Industries	
141 Mong Way	
P.O. Box 53	
Reno PA 16343	
USA	Supplier Code
Attn:	Ph: 800-327-9413

**Test Report#: 8672**    **Entry Date:** Friday, April 20, 2012

**Contact:** Andy Kockler

**PO#:** PUR363

*Hydrogen Embrittlement Testing IAW ASTM F519-10.*

*Requirements: When tested in accordance with 4.5.4, the baked parts shall not crack or fracture. Bars were loaded at 75% of nominal notch tensile strength.*

Part Test Information										
PART NUMBER	LOT NUMBER		S#	SAMPLE DESCRIPTION						
TEST SPECIFICATION NAME	TEST PROCEDURE NAME			HOURS	CYCLES					
TEST RESULTS	INDATE	OUTDATE	TESTCNT	RETCNT	REQ	COMP	REQ	HOURS	COMP	
<b>Test Bars</b>										
Hydrogen Embrittlement ASTM F519-10										
	23-Apr-12	01-May-12	4	4	200	200				
<i>Results: PASS - Samples were exposed for 200 hours IAW ASTM F519 with no fracture.</i>										
<b>Test Bars</b>										
Hydrogen Embrittlement ASTM F519-10										
	23-Apr-12	01-May-12	4	4	200	200				
<i>Results: PASS - Samples were exposed for 200 hours IAW ASTM F519 with no fracture.</i>										

Michele Singer

Revision# 1.10 Date 12/16/10

End Of Report

Quality Assurance Administrator

The results stated above relate only to the specific items tested. Information and statements in this report are derived from material, information, and/or specifications furnished by the client and exclude any expressed or implied warranties as to the fitness of material tested or analyzed for any particular purpose or use. This report is confidential property of our client and may not be used for advertising purposes. This report shall not be reproduced except in full, without written approval of this laboratory. This recording of false, fictitious or fraudulent statements or entries on this document may be punished as a felony. Sample remnants are retained for a minimum of 6 months following issuance of test results, at which point they will be discarded unless notified in writing by the client. Any client claims or damages arising from the use of information in this report are strictly limited to the cost of the services provided by Assured Testing Services.